



Specification 其他產品規格

Stainless Steel U Channel

不銹鋼槽鐵

U Channel Type	Thickness (mm)		3.0	3.0	5.0/6.0	8.0/9.0	10.0	12.0/13.0	15.0~19.0	20.0~25.0
	Height H (mm)	Min.	20	25	32	45	50	65	105	130
		Max.	737							
	Width W (mm)		$W \geq (H+25+t)$							
	Edge Width B (mm)	Min.	20	25	32	45	65	65	-	-
		Max.	50	50	50	100	100	100	-	-
	Height H (mm)	Min.	140	140	140	200	200	200	-	-
	Width W (mm)		$W \geq (H+25+t)$						-	-

Chemical Composition of Stainless Steel Pipe

不銹鋼鋼管化學成份表

Standard & Grade		Chemical Composition (%)								Solution Heat Treating Condition
		C	Si	Mn	P	S	Ni	Cr	Mo	
ASTM A312	TP304	≤0.080	≤1.00	≤2.00	≤0.045	≤0.030	8.0~11.0	18.0~20.0	-	Annealing Requirement 1040°C Min. Water Quenching
	TP304L	≤0.035	≤1.00	≤2.00	≤0.045	≤0.030	8.0~13.0	18.0~20.0	-	
	TP316	≤0.080	≤1.00	≤2.00	≤0.045	≤0.030	10.0~14.0	16.0~18.0	2.0~3.0	
	TP316L	≤0.035	≤1.00	≤2.00	≤0.045	≤0.030	10.0~14.0	16.0~18.0	2.0~3.0	
JIS G3459	SUS304TP	≤0.080	≤1.00	≤2.00	≤0.045	≤0.030	8.0~11.0	18.0~20.0	-	Solution Treatment 1010°C Min. Rapid Cooling
	SUS304LTP	≤0.030	≤1.00	≤2.00	≤0.045	≤0.030	9.0~13.0	18.0~20.0	-	
	SUS316TP	≤0.080	≤1.00	≤2.00	≤0.045	≤0.030	10.0~14.0	16.0~18.0	2.0~3.0	
	SUS316LTP	≤0.030	≤1.00	≤2.00	≤0.045	≤0.030	12.0~16.0	16.0~18.0	2.0~3.0	
CNS 6331	304TP	≤0.080	≤1.00	≤2.00	≤0.045	≤0.030	8.0~11.0	18.0~20.0	-	Solution Treatment 1010°C Min. Rapid Cooling
	304L1TP	≤0.035	≤1.00	≤2.00	≤0.045	≤0.030	8.0~13.0	18.0~20.0	-	
	304L2TP	≤0.030	≤1.00	≤2.00	≤0.045	≤0.030	9.0~13.0	18.0~20.0	-	
	316TP	≤0.080	≤1.00	≤2.00	≤0.045	≤0.030	10.0~14.0	16.0~18.0	2.0~3.0	
	316L1TP	≤0.035	≤1.00	≤2.00	≤0.045	≤0.030	10.0~14.0	16.0~18.0	2.0~3.0	
	316L2TP	≤0.030	≤1.00	≤2.00	≤0.045	≤0.030	12.0~16.0	16.0~18.0	2.0~3.0	